

FACESTOCK DESCRIPTION: 2.6 MIL WHITE POLYPROPYLENE

A white polypropylene film with a pearlescent sheen. It is very durable with high opacity and is biaxially oriented with good stiffness for conversion and automatic label dispensing.

Caliper, mils	2.6
Yield, sq. in/lb	15,000
Opacity, %	88
Tensile Strength, MD / TD, psi	13,100 / 27,700
Tensile Elongation, MD / TD, %	200 / 50
Stiffness, Gurley, MD / TD, mg	22 / 42
Dimensional Stability, MD / TD, %	-5.0 / -5.0
Regulatory Compliances	ASTM F963 Child Toy Safety, California Proposition 65, CONEG, Non-ozone Depleting, RoHS

ADHESIVE DESCRIPTION:

An excellent removable adhesive with low to moderate adhesion on most surfaces, it is a good choice for a variety of removable applications. It functions most effectively on smooth surfaces, including glass, paper and painted metal. It has excellent stability and demonstrates very little growth in adhesion over time however, adhesion growth will vary depending upon substrate. Pretesting is recommended to determine end-use applicability.

Type	Ultra-Removable
Classification	Emulsion Acrylic
pH	Neutral to Slightly Alkaline
Minimum Application Temp., °F	-10
Service Temperature Range, °F	-40 to +160
Regulatory Compliances	Acute Oral Toxicity 16 CFR 1500.3, ASTM F963 Child Toy Safety, CONEG, CPSIA, FDA 21 CFR 175.105, Primary Eye Irritant 16 CFR 1500.42, Primary Skin Irritant 16 CFR 1500.41, RoHS

LINER DESCRIPTION: 40#

A supercalendered bleached liner. Superior die-cutting and stripping properties. Recommended for roll-to-roll applications. Good back printability.

Basis Weight (25 x 38 / 500), lbs.	44.7
Caliper, mils	2.5
Brightness, %	78
Gloss, 75°, %	48
Opacity, %	65
Tear, MD / CD, g	32 / 34
Tensile, MD / CD, lbs.	34 / 22
Regulatory Compliances	ASTM F963 Child Toy Safety, CONEG, REACH, RoHS

All product specifications are for informational use only. Each customer and/or end user should determine the suitability of any product for their particular application. The above specifications are based on typical values and most current information. Specific products listed were current at the time of publication, however, all raw materials are subject to change.

Shelf Life: Six months when stored at 72°F / 50% RH.

Updated: June 2013